[illegible]

[illegible] [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible]

1) [illegible] 31 [illegible]-[illegible] [illegible]

2) [illegible]

3) [illegible], [illegible]

KXG [illegible]

[illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible], [illegible]-[illegible] [illegible]

KXG	Online coated reflective glass performance data										
Color	Thickness	Visible Light Transmittanc	Visible Light Reflectance	UV Light Transmittanc e	Direct Light Transmittanc e	Direct Light Reflectance	Total Solar Transmittanc e	Shading Coeffcient (SC)	RHG	K Value (Summer Daytime)	K Value (Winter Night)
Euro Bronze	5mm	25.78%	16.60%	2.73%	35.79%	14.70%	47.73%	0.54	0.505	5.272	5.843
	6mm	20.45%	16.32%	2.03%	29.70%	14.85%	43.08%	0.48	0.463	5.243	5.808
Euro Grey	5mm	24.96%	15.62%	3.85%	32.98%	14.02%	45.76%	0.51	0.488	5.272	5.843
	6mm	21.26%	15.36%	3.05%	28.01%	13.37%	42.15%	0.47	0.457	5.243	5.808
Dark Grey	5mm	24.93%	17.13%	4.68%	32.67%	15.22%	45.24%	0.51	0.482	5.272	5.843
	6mm	20.82%	14.09%	3.50%	27.39%	12.71%	41.83%	0.47	0.455	5.243	5.808
Light Blue	5mm	28.47%	31.89%	4.39%	30.29%	22.01%	41.80%	0.47	0.445	5.256	5.824
	6mm	25.33%	31.63%	3.54%	28.14%	21.17%	38.85%	0.44	0.419	5.243	5.808
Dark Blue	5mm	23.35%	13.46%	12.07%	43.49%	18.44%	52.68%	0.59	0.548	5.272	5.843
	6mm	18.79%	11.79%	10.23%	38.68%	17.19%	49.32%	0.55	0.517	5.243	5.808
F-Green	5mm	28.40%	35.11%	3.13%	24.11%	19.91%	37.61%	0.42	0.409	5.272	5.843
	6mm	26.43%	34.12%	2.76%	20.76%	18.66%	35.37%	0.40	0.39	5.243	5.808
Dark Green	5mm	27.31%	26.52%	4.36%	28.14%	16.63%	41.46%	0.47	0.446	5.272	5.843
	6mm	25.40%	24.35%	4.06%	26.15%	15.15%	40.30%	0.45	0.438	5.243	5.808
Silver White	5mm	50.58%	34.10%	13.87%	58.00%	25.85%	61.89%	0.70	0.625	5.272	5.843
	6mm	42.75%	38.11%	9.47%	52.31%	28.29%	56.99%	0.64	0.578	5.243	5.808
For reference only											

KXG □□□□□□

1) □□□□□□□□□□□□□□□ □□□□ □□□□ □□□□ □□□□ □□ □□□□□ □□□□□ □□□□□□□ □□□ □□ □'□ □□□□□ □, □□ □□□□□□□ □□□□ □□□□ □□ □□□□ □□ □□□□□□□□□□ □□□□□ □□□□ □□□ □□ □'□ □□□ □□□□□□, □□□□□□ □ □□□□□, □□□□□□□□□□□ □□□ □□□□□□□ □□□□□□ □□□□□□□□□ □□□, □□□□ □□□□□□□ □□□□□□□ □□□□□□□,

2) □□□□ □□□□□□□□□□□ □□□□□□□□□ □□□□□□□□□ □□□, □□□ □□□□□□□□ ± 0.3 □□□□, □□□ □□□□ ± 1 □□□□;

3) □□□□□□ □□□□ □□□□□□□□□ □□□□□ □□□□□□□ □□□□□ □□□□□, □□□ □□□□□□□ □□□□□□□ □□□□□□□□□ □□□□□□□ □□□□□ □□□□□ □□□□□□□ □□□ □□ □□ □□□□□□□ □□□□ □□□□ □□ □□□□ □□ □□□□□□□ □□□□□□□ □□□□ □□□□□ □□□□□ □□□□□□ □□ □□;

4) □□□□□□ □□□□□ ISO, □□□, □□□□□□, □□□□□□, ANSI □□□ 97.1, AS/NZS 2208 □□□□□□□ □□□□□□ □□□□□□□□□ is

5) □□□□□□ □□□□□□ □□□ □□ □□ □□□□□□□ □□□□ □□□□ □□□□□ □□□□□ □□□□ □□ □□□□□□□ □□□□ □□□□□;

6) □□□□□□□ □□□□□□□□ □□□ □□□□□ □□□□□□□□ □□□□ □□□□□□□□□ □□□□□□□□□□ □□□□□ □□□□□ □□□□□ □□□□□□ □□□□□□□ □□□ □□□

KXG □□□□□□□

1) □□□□□□□□□□ □□□□ □□□□, □□□□□□□ □□□ □□□□□□□ □□□□□□ □□□□□□□□ 7-15 □□□ days □□□ □□□ □□□ □□□□□ □□ □□□ □□□□ □□□ □□□□□ □□□□ 7 □□□□□ □□□□□ □□□ □□□□ □□□□ □□□□□□□□□ □□□□□□ □□□□ □□□□□

2) □□□□□ □□□□□□□□ □□□□□ □□□□ □□□□□□□□□ □□□□□ □□□□ □□□□ □□□□□□ □□□□□□ □□□□ □□□□ □□□□□□ □□□□□ □□□□□□□ □□□□ □□□□□□□□□□□ □□□□□□□□□ □□□□□□□ □□□□□□ □□□□□□

3) □□□□□□ □□□□ □□□□□□□ □□□□ □□□□ □□□□□□□ □□ □□□□□ □□ □□□□□ □□ □□□□□ □□□□□□□□□□□□ □□□□ □□□□ □□□□□

4) □□□ □□□□□□□□□□□□ □□□□□ □□ □□ □□□□□ □□□□□□ □□ □□□ □□□□ □□□□□□□ □□□□□ □□□□□ □□□□□□□ □□ □□□□□□□□□□□ □□□□

□□□□ □□□ □□□□ □□□□□□□ □□□□□ □□□□□□□□□□□□ □□ □□□□ □□□□□□□ □□□□□□□ □□□ □□□□ □□□□□□ □□□□□□ □□□□□ □□□□□□, □□□ □□□□□□ □□□□ □□□□□□□□□□ □□□□□□ □□□□ □□□□□□□□□ □□□□□