5 □□□□ 6 □□□□ □□□□□ □□□□ □□ dark◌□ □□□□ □□□□□□ □□□□□□□□□ □□□□□ □□□□□□□

5 □□□□ 6 □□□□ □□□□□ □□□□□□□□□ □□□, □□ dark◌□ □□□□ □□□□□□□□□ □□□□□, □□ dark◌□ □□□□ □□□□□□□ □□□□, 5 □□□□ 6 □□□□ □□□□□ □□□□□-□□□□□□□□□ □□□□□□□□□ □□□□□□□ □□□□□, 5 □□□□ 6 □□□□ □□□□□ □□□-□□□□□□□□□ □□□□□□□ □□□□□□ □□□□□□□□□□ □□□□□, 5 □□□□ 6 □□□□ □□ dark◌□ □□□□ □□□□ □□□□□□□□ □□□□□□□ □□□□□, □□□□□□□ □□□□ □□□□□ 5 □□□□ □□ dark◌□ □□□□ □□□□□ 6 □□□□ □□ dark◌□ □□□□ □□□□ □□□□□□ □□□□□□ □□□ □□□□□□□□□□□□ □□□□ □□□□□ □□□□□□□□□□ □□□□ □□□ □□□□ □□, □□□ □□□□□□ □□□□□□□□□ □□□□□ □□□□□ □□□□□□□ □□□□□, □□□□□□□□□□ □□□□ □□□□□, □□□□□□□□ □□□□□□□□□ □□□□□ □□□□□□ □□□□□□□□□□ □□□□□□□

Kunxing □□□□□ □□□□□□□□□ □□□□□□□ □□□□□□

- □□□□□□□: 5 □□□□ 6 □□□□ □□□□□ □□□□□□□□□□□□□□ 5 □□□□ 6 □□□□ □□□□□ □□□□ □□□□□ □□□□ 3 □□□□ 5 □□□ □□□□□

- UV- □□□□□□□□□□□, □□□-□□□□□□□□□□: 5 □□□□ 6 □□□□ □□□□□ □□□□□□□□□ □□□□□, □□□□□□□□-□□□□□□□□□ □□□ □□□-□□□□□□□□□ □□□□□□□□□ □□ 5 + 5 □□□□ 5 + 6 □□□□ 6 + 6 □□□□ □□□□□ □□□□□□□ □□□□□ □□□□□□□ □□□□□□□□□□□□□ □□□□□ □□□□□□ □□□□□ □□□□ □□□□ □□□□□ □□□□ □□□□ □□□□ □□□ □□□ □□□ □□□□□□□□□□□ □□□ isenergy- □□□□□□□ □□□□□□

- □□□□□□□: □□□ □□□□□□□ □□□□□□ □□□□□□ □□□□□ □□□ □□□□□□ □□□ □□□ □□□□ □□□□□□□□ □□□□□ □□□□□□□, □□□□□□□□ □□□□□□□□□□□ □□□□□ □□□

- □□□□□ □□□□□ □□□ □□□□□□□□□□□ □□□□□□□□□ □□□□□ □□□□□□□ □□□□ □□□□□

- □□□□□□□□□□ □□□ □□□□ □□□□□□ □□□□ □□□□□□□□□ □□□□□□□□□□□□

Tinted float glass performance data

Color	Thickness	Visible Light Transmittance	Visible Light Reflectance	UV Light Transmittance	Direct Sinlight Transmittance	Direct Sunlight Reflectance	Total Solar Transmittance	Shading Coeffcient (SC)	RHG	K Value (Summer Daytime)	K Value (Winter Night)
Euro Bronze	5mm	51.94%	6.44%	14.52%	51.78%	6.69%	62.50%	0.70	0.84	5.64	5.272
	6mm	47.15%	6.73%	11.83%	46.87%	6.79%	58.83%	0.66	0.83	5.606	5.243
Euro Grey	5mm	51.66%	6.36%	20.29%	49.19%	6.48%	60.63%	0.68	0.84	5.623	5.272
	6mm	45.24%	6.06%	16.47%	42.98%	6.15%	56.11%	0.63	0.84	5.582	5.243
Dark Grey	5mm	47.90%	6.77%	19.87%	46.96%	6.75%	58.91%	0.66	0.84	5.606	5.272
	6mm	41.96%	6.59%	16.54%	41.37%	6.53%	54.82%	0.62	0.83	5.569	5.243
Light Blue	5mm	71.07%	7.78%	26.60%	53.99%	6.94%	64.07%	0.72	0.654	5.272	5.843
	6mm	67.74%	7.69%	24.13%	50.67%	6.96%	61.61%	0.69	0.632	5.243	5.808
F-Green	5mm	74.60%	8.03%	24.54%	48.75%	6.67%	60.26%	0.68	0.619	5.272	5.843
	6mm	71.36%	7.66%	20.22%	43.72%	6.35%	56.60%	0.64	0.586	5.243	5.808

For reference only

5 □□□□ 6 □□□□ □□ dark◌□ □□□□ □□□□ □□□□□□ □□□□□□□□□□□□□□

1. □□□: 5 □□□□ 6 □□□□

□. □□□□: □□□□□□□□ □□□□ 2440 * 3660 □□□□, □□□□□□□□ □□□□□□□□□□□□□ □□□□□□□ □□□□□□□□□ □□□ □□□

□. □□□□□ □□□□□□□□□□□□□: □□□□□□ □□□□ □□□ □□□□□□□, □□□□□, □□□□□□□□□□ □□□□□□□□□, □□□□□□ □□□□□□ □□□ □□□ □□□□□ t □□□ □□□□ □□□□□□ □□ dark◌□ □□□□ □□□□ □□□□□□□□□ is □□□□ □□□□□ □□ dark◌□ □□□□ □□□□□□□□□ □□□□□□ □□□□□ □□□

5 □□□□ 6 □□□□ □□ dark◌□ □□□□ □□□□□□□□□ □□□□□□□ □□□□□□□

1. □□□□□ □□□, □□□□□ □□□□□ □□□□□□, □□□□□ □□□□□□□ □□□□□, □□□□□ □□□□□□□□□ □□□□□□

2. □□□□□, □□□□□□, □□□□, □□□□□□ □□□□□

□□□□□ □□□□ □□□□□□□ □□□ □□□□□□□ □□□□□ KXG

KXA
清扫清洁