





Glass Type	Visible Light	Visible Light Ref(%)	Sunlight Trans (%)	Sunlight Ref (%)	SC	Solar Energy Trans (%)
4mm Euro Grey	56.60	7.73	56.20	9.59	0.79	65.03
5mm Euro Grey	48.80	6.59	48.00	7.95	0.73	59.37
6mm Euro Grey	43.98	14.11	43.47	13.20	0.67	54.65
4mm Dark Grey	35.08	6.39	42.45	8.46	0.49	55.12
5mm Dark Grey	27.15	6.12	34.48	7.78	0.62	49.38
6mm Dark Grey	21.33	5.62	28.79	7.04	0.56	45.35
4mm Pink Glass	77.67	9.00	77.63	11.65	0.37	80.40
5mm Pink Glass	74.75	8.78	74.75	11.02	0.90	78.42
6mm Pink Glass	69.88	8.35	70.62	10.40	0.88	75.52
4mm Dark Blue	50.21	6.74	58.17	9.03	0.75	66.63
5mm Dark Blue	42.87	6.71	52.22	8.56	0.70	62.34
6mm Dark Blue	37.21	6.47	46.78	8.11	0.66	58.42
4mm Ford Blue	66.11	8.63	62.80	10.15	0.78	69.78
5mm Ford Blue	62.12	8.12	59.14	9.34	0.76	67.28
6mm Ford Blue	56.98	7.99	53.94	9.14	0.71	63.47
4mm F-Green Glass	79.37	9.37	54.70	9.17	0.72	64.02
5mm F-Green Glass	75.21	8.86	47.40	8.19	0.66	58.86
6mm F-Green Glass	72.53	8.70	42.19	8.02	0.62	55.04





